

PART NO. 614000UNE

A-02YST2Y Outdoor Telephone Cable, 0.40 mm

CAMCOM™

Detailed Specifications & Technical Data

CROSS SECTION



1 Conductor
2 Insulation
3 Stranding
4 Wrapping
5 Messenger Wire
6 Outer Jacket

CABLE CONSTRUCTION

Conductor	: Electrolytic annealed solid copper (CCITT Yellow Book Vol. III-2-G.541 B article, IEC 28 and ASTM B 3).
Insulation	: Color coded foam skin polyethylene cladded with solid polyethylene (BS 6234 Type 03 – ASTM D 1248).
Stranding	: Star quads or pairs are assembled into 10 pairs units. Groups having 25, 50 or 100 pairs are stranded together.
Wrapping	: A non-hygroscopic and dielectric polyester tape is applied on the cable core longitudinally or helically.
Messenger Wire	: Galvanized steel messenger wire (ASTM A 475-66T).
Outer Jacket	: Linear low-density or medium-density, UV resistant black polyethylene outer jacket (ASTM D 1248).

TECHNICAL DATA

Conductor Diameter	: 0.40 mm
Conductor Resistance Ω/km (20 °C) – Maximum Average	: 139,4
Conductor Resistance Ω/km (20 °C) – Maximum Individual	: 146,6
Insulation Resistance MΩ/km (500 VDC)	: >10000
Mutual Capacitance nF/km (800 Hz) – Maximum Average	: 50
Mutual Capacitance nF/km (800 Hz) – Maximum Individual	: 56
Capacitance Unbalance pF/500 m – Between Pairs – Maximum Average	: 125
Capacitance Unbalance pF/500 m – Between Pairs – Maximum Individual	: 350
Between Adjacent Quads – Maximum Average	: 125
Between Adjacent Quads – Maximum Individual	: 275
To Screen – Maximum Average	: 500
To Screen – Maximum Individual	: 2000
Dielectric Strength – V (DC, 1 minute) – Pair – Pair	: 1400
Dielectric Strength – V (DC, 1 minute) – Pair – Screen	: 1400

CABLE TYPE DATA

CAMCOM Part No.	Conductor Size / Type
614000UNE	0.40 mm

PRODUCT VIEW



Camcom is proud to be certified by

Frame Offices - HQ, Alexanderveld 5-9,
2585 DB, Den Haag, Netherlands
+31708910864
sales@camcom.co.nl

Designed in Netherlands & Produced Globally.

Prepared By : Steve Smith

Disclaimer :- Datasheet is subject to modification without prior notication

© Technovation Alliance Enterprise B.V.