

PART NO. 871032CBA

A-DF(ZN)(SR)2Y Fiber Optic Cable, 32F OM1

Detailed Specifications & Technical Data

CROSS SECTION



1 Optical fiber core [1]
2 Waterproof thixotropic jelly
3 PBT Tube
4 Non-metallic central strength member
5 Jelly filling6
6 Non-metallic strength member (Glass
7 Ripcord
8 Corrugated steel tape

APPLICATION

Minimum Bending Radius – Operation	: 20 x cable Ø
Minimum Bending Radius – Fixed	: 15 x cable Ø
Temperature Range – Storage	: -40°C to +70°C
Temperature Range – Installation	: -30°C to +60°C
Temperature Range – Transport	: -40°C to +70°C
Temperature Range – Operating	: -40°C to +70°C

CABLE CONSTRUCTION

Optical fiber core [1]
Waterproof thixotropic jelly
PBT Tube
Non-metallic central strength member (FRP)
Jelly filling6 : Core Wrapping (Polyester Tape)
Non-metallic strength member (Glass yarn).
Ripcord
Corrugated steel tape
UV resistant polyethylene (HDPE) black outer jacket

MARKING, PACKING & DELIVERY

Marking	: CAMCOM – Date of Manufacture – Fiber Count and Type – Length Marking
Packing	: Wooden drum with protection
Delivery Lengths	: 2 km, 4 km ± %5 tolerance

MECHANICAL & ENVIRONMENTAL CHARACTERISTICS

	Test Standard	Specified Value	Acceptance Criteria
Maximum Installation Tension [2]	IEC 60794-1-2-E1	1.0 x W(N), min. 1200 N	Fiber strain ≤ 0.33%
Maximum Operation Tension	IEC 60794-1-2-E1	0.5 x W(N), min. 600 N	Δα ≤ 0.05 dB, No fiber strain
Crush Strength	IEC 60794-1-2-E3	3000 N / 100 mm, maks. 15 min	Δα ≤ 0.05 dB, No damage
Impact	IEC 60794-1-2-E4	10 Nm, 3 darbe, R= 300 mm	Δα ≤ 0.05 dB after the test
Torsion	IEC 60794-1-2-E7	1 m, 100N, +/- 180°, 10 cycles	Δα ≤ 0.05 dB, No damage
Repeated Bending	IEC 60794-1-2-E6	R=20x D, 100 N, 35 cycles	No damage
Bending Radius	IEC 60794-1-2-E11	R=20x D, 4 turns, 3 cycles	Δα ≤ 0.05 dB, No damage
Temperature Cycling	IEC 60794-1-2-F1	-20°C to +70°C	Δα ≤ 0.05 dB/km
Waterproofness	IEC 60794-1-2-F5B	Sample= 3 m, water column= 1 m	No water leakage in 24 hours.

CABLE TYPE DATA

CAMCOM Part No.	Construction	Conductor Size / Type	Item Size	Approx. Cable Ø (mm)	Approx. Weight (kg/km)
871032CBA	32 Fibers	OM1	32F OM1	11.4	146

Camcom is proud to be certified by

Frame Offices - HQ, Alexanderveld 5-9,
2585 DB, Den Haag, Netherlands
+31708910864
sales@camcom.co.nl

Designed in Netherlands & Produced Globally.

Prepared By : Steve Smith

Disclamer :- Datasheet is subject to modification without prior notication

© Technovation Alliance Enterprise B.V.