


PART NO. 881024GAA

U-D(ZN)H Fiber Optic Cable, 24F OM1

Detailed Specifications & Technical Data

CROSS SECTION



1 Optical fiber core [1]
2 Waterproof thixotropic jelly
3 PBT Tube
4 Non-metallic strength member (Aramid
5 UV resistant halogen-free (LSOH) outer

CABLE CONSTRUCTION

Optical fiber core [1]
Waterproof thixotropic jelly
PBT Tube
Non-metallic strength member (Aramid yarn)
UV resistant halogen-free (LSOH) outer jacket

MARKING, PACKING & DELIVERY

Marking : CAMCOM – Date of Manufacture – Fiber Count and Type – Length Marking
Packing : Wooden drum with protection
Delivery Lengths : 2 km, 4 km ± %5 tolerance

APPLICATION

Minimum Bending Radius – Operation : 20 x cable Ø
Minimum Bending Radius – Fixed : 15 x cable Ø
Temperature Range – Storage : -40°C to + 70°C
Temperature Range – Installation : -30°C to +60°C
Temperature Range – Transport : -40°C to + 70°C
Temperature Range – Operating : -30°C to +60°C

MECHANICAL & ENVIRONMENTAL CHARACTERISTICS

	Test Standard	Specified Value	Acceptance Criteria
Maximum Installation Tension [2]	IEC 60794-1-2-E1	Max. 650 N	Fiber strain ≤ 0.33%
Maximum Operation Tension		Max. 200 N	Δα ≤ 0.05 dB, No fiber strain
Crush Strength	IEC 60794-1-2-E3	200 N / 100 mm, maks. 15 min	Δα ≤ 0.05 dB, No damage
Impact	IEC 60794-1-2-E4	10 Nm, 3 impacts, R= 300 mm	Δα ≤ 0.05 dB after the test
Torsion	IEC 60794-1-2-E7	1 m, 100N, +/- 180°, 10 cycles	Δα ≤ 0.05 dB, No damage
Repeated Bending	IEC 60794-1-2-E6	R=20x D, 100 N, 35 cycles	No damage
Bending Radius	IEC 60794-1-2-E11	R=20x D, 4 turns, 3 cycles	Δα ≤ 0.05 dB, No damage
Temperature Cycling	IEC 60794-1-2-F1	-20°C to +70°C	Δα ≤ 0.05 dB/km
Waterproofness	IEC 60794-1-2-F5B	Sample= 3 m, water column= 1 m	No water leakage in 24 hours.

CABLE TYPE DATA

CAMCOM Part No.	Construction	Conductor Size / Type	Item Size	Approx. Cable Ø (mm)	Approx. Weight (kg/km)
881024GAA	24 Fibers	OM1	24F OM1	8	69

PRODUCT VIEW



Camcom is proud to be certified by

Frame Offices - HQ, Alexanderveld 5-9,
2585 DB, Den Haag, Netherlands
+31708910864
sales@camcom.co.nl

Designed in Netherlands & Produced Globally.

Prepared By : Steve Smith

Disclamer :- Datasheet is subject to modification without prior notication

© Technovation Alliance Enterprise B.V.